

CEMENT ALL®

Multi-Purpose Repair Material & Non-Shrink Grout



PRODUCT DATASHEET

DESCRIPTION: Rapid Set® CEMENT ALL® is a high-performance, fast-setting, multi-purpose concrete repair material and non-shrink grout. Durable in wet environments, CEMENT ALL is a blend of Rapid Set hydraulic cement and specially graded fine aggregates. CEMENT ALL is non-metallic and no chlorides are added. Mix CEMENT ALL with water to produce a workable, high quality material that is ideal where rapid strength gain and high durability are desired. CEMENT ALL sets in 15 minutes and achieves structural strength in 1 hour.*

USES: Use CEMENT ALL for general and structural concrete repair, doweling and anchoring, industrial grouting, formed work, vertical and horizontal trowel applications. CEMENT ALL is ideal for airport, highway, industrial and marine applications.

ENVIRONMENTAL ADVANTAGES: Use CEMENT ALL to reduce your carbon footprint and lower your environmental impact. Production of Rapid Set cement emits far less CO₂ than portland cement. Contact your representative for LEED values and environmental information.

APPLICATION: Apply CEMENT ALL in thicknesses from featheredge to 4" (10 cm). For heavy loads and vehicle traffic, minimum thickness will vary. Not intended for high heat applications above 300°F (149°C). For deeper sections, use Rapid Set® Mortar Mix or Rapid Set® Concrete Mix. For overlay applications, a minimum of one test section should be prepared to evaluate the suitability of the materials and procedures.

SURFACE PREPARATION: For repairs, application surface shall be clean, sound and free from any materials that may inhibit bond, such as oil, asphalt, curing compound, acid, dirt and loose debris. Roughen surface and remove all unsound material. Apply CEMENT ALL to a surface that is thoroughly saturated with no standing water.

MIXING: The use of a power-driven mechanical mixer, such as a mortar mixer or a drill-mounted mixer, is recommended. Organize work so that all personnel and equipment are in place before mixing. Use clean potable water. CEMENT ALL may be mixed using 3 to 5 quarts (2.8 L to 4.7 L) of water per 55-lb (25-kg) bag. Use less water to achieve higher strengths. Do not exceed 5 quarts (4.7 L) of water per bag. For increased fluidity and workability, use Rapid Set® FLOW Control® plasticizing admixture from the Rapid Set® Concrete Pharmacy®. Place the desired quantity of mix water into the mixing container. While the mixer is running, add CEMENT ALL. Mix for the minimum amount of time required to achieve a lump-free, uniform consistency (usually 1 to 3 minutes). Do not retemper.

PLACEMENT: CEMENT ALL may be placed using traditional construction methods. Organize work so that all personnel and equipment are ready before placement. Place, consolidate and screed quickly to allow for maximum finishing time. Use a method of consolidation that eliminates air voids. Do not wait for bleed water; apply final finish as soon as possible. CEMENT ALL may be troweled, floated or broom finished. On flat work, do not install in layers. Install full-depth sections and progress horizontally. Do not install on frozen surfaces. To extend working time, use Rapid Set® SET Control® retarding admixture from the Concrete Pharmacy or cold mix water. CEMENT ALL may be applied in temperatures ranging from 45°F to 90°F (7°C to 32°C).

HIGHLIGHTS

FAST

Sets in 15 minutes
Structural strength in 1 hour*

STRONG

3 times stronger than most concrete

DURABLE

Formulated for long life in critical applications

EXCELLENT BOND

Superior adhesion to concrete, stone, brick, block, stucco and more

STRUCTURAL

For repair and new construction

MULTI-PURPOSE

Use for concrete repair, grouting, anchoring, casting, underlayment and more

CONFORMS TO:

ASTM: C1107, C928, C387 and CRD C621
State and Local Approvals
Army Corps of Engineers

MANUFACTURER:

CTS Cement Manufacturing Corp.
11065 Knott Ave., Suite A
Cypress, CA 90630
800-929-3030
Fax 714-379-8270
www.CTScement.com
info@CTScement.com



CEMENT ALL® Multi-Purpose Repair Material & Non-Shrink Grout

CURING: Water cure all Rapid Set® CEMENT ALL® installations by keeping exposed surfaces wet for a minimum of 1 hour. Begin curing as soon as the surface starts to lose its moist sheen. When experiencing extended setting time due to cold temperature or the use of retarder, longer curing times may be required. The objective of water curing shall be to maintain a continuously wet surface until the product has achieved sufficient strength.

COLD WEATHER: Environmental and material temperatures below 70°F (21°C) may delay setting time and reduce the rate of strength gain. Lower temperatures will have a more pronounced effect. Thinner sections will be more significantly affected. To compensate for cold temperatures, keep material warm, use heated mix water, and follow ACI 306 Procedures for Cold Weather Concreting.

WARM WEATHER: Environmental and material temperatures above 70°F (21°C) may speed setting time and increase the rate of strength gain. Higher temperatures will have a more pronounced effect. To compensate for warm temperatures, keep material cool, use chilled mix water, and follow ACI 305 Procedures for Hot Weather Concreting. The use of SET Control retarding admixture from the Concrete Pharmacy will help offset the effects of high temperatures.

YIELD & PACKAGING: CEMENT ALL is available in 55-lb, 25-lb and 10-lb (25-kg, 11.3-kg and 4.5-kg) sizes. One 55-lb (25-kg) bag of CEMENT ALL will yield approximately 0.5 ft³.

SHELF LIFE: CEMENT ALL has a shelf life of 12 months when stored properly in a dry location, protected from moisture, out of direct sunlight, and in an undamaged package.

USER RESPONSIBILITY: Before using CTS products, read current technical data sheets, bulletins, product labels and safety data sheets. It is the user's responsibility to review instructions and warnings for any CTS products prior to use.

WARNING: DO NOT BREATHE DUST. AVOID CONTACT WITH SKIN AND EYES. Use material in well-ventilated areas only. Exposure to cement dust may irritate eyes, nose, throat, and the upper respiratory system/lungs. Silica exposure by inhalation may result in the development of lung injuries and pulmonary diseases, including silicosis and lung cancer. Seek medical treatment if you experience difficulty breathing while using this product. The use of a NIOSH/MSHA-approved respirator (P-, N- or R-95) is recommended to minimize inhalation of cement dust. Eat and drink only in dust-free areas to avoid ingesting cement dust. Skin contact with dry material or wet mixtures may result in bodily injury ranging from moderate irritation and thickening/cracking of skin to severe skin damage from chemical burns. If irritation or burning occurs, seek medical treatment. Protect eyes with goggles or safety glasses with side shields. Cover skin with protective clothing. Use chemical resistant gloves and waterproof boots. In case of skin contact with cement dust, immediately wash off dust with soap and water to avoid skin damage. In case of skin contact with wet concrete, wash exposed skin areas with cold running water as soon as possible. In case of eye contact with cement dust, flush immediately and repeatedly with clean water, and consult a physician. If wet concrete splashes into eyes, rinse eyes with clean water for at least 15 minutes and go to the hospital for further treatment.

PROPOSITION 65 WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. Please refer to the SDS and www.CTScement.com for additional safety information regarding this material.

LIMITED WARRANTY: CTS CEMENT MANUFACTURING CORP. (CTS) warrants its materials to be of good quality and, at its option, will replace or refund the purchase price of any material proven to be defective within one (1) year from date of purchase. The above remedies shall be the limit of CTS's responsibility. Except for the foregoing, all warranties expressed or implied, including merchantability and fitness for a particular purpose, are excluded. CTS shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the materials.

PHYSICAL DATA

Set Time, ASTM C191 Mod.**

Initial set	15 minutes
Final set	35 minutes

Compressive Strength, ASTM C109 Mod.**

1 hour*	3000 psi (20.7 MPa)
3 hours	5000 psi (34.5 MPa)
24 hours	6000 psi (41.4 MPa)
7 days	7000 psi (48.3 MPa)
28 days	9000 psi (62.1 MPa)

Slant Shear Bond, ASTM C882 Mod.**

24 hours	1500 psi (10.3 MPa)
28 days	2500 psi (17.2 MPa)

Splitting Tensile, ASTM C496 Mod.**

7 days	700 psi (4.82 MPa)
28 days	880 psi (6.06 MPa)

Flexural Strength, ASTM C78 Mod.**

7 days	600 psi (4.14 MPa)
28 days	800 psi (5.51 MPa)

*After final set
 **Data obtained at flow consistency 102 by ASTM C1437
 All data produced at 70°F (21°C)

