

SKIM COAT

For Patching, Skim Coating & Underlayments



PRODUCT DATASHEET

DESCRIPTION: Rapid Set SKIM COAT is a smooth (unsanded), fast curing, hydraulic cement-based floor underlayment. Use under flooring for concrete repairs, patching and skim coating on interior and exterior projects. Apply from featheredge to 1" (2.5 cm).

USES: Use SKIM COAT to repair, level and smooth concrete substrates prior to the installation of floor coverings such as VCT, sheet vinyl, carpet, tile, pavers, and other protective toppings.

ENVIRONMENTAL ADVANTAGES: Use SKIM COAT to reduce your carbon footprint and lower your environmental impact. Production of Rapid Set cement emits far less CO₂ than portland cement. Contact your representative for LEED values and environmental information.

APPLICATION: Apply Skim Coat in thicknesses from featheredge to 1" (2.5 cm). Most floor coverings can be installed over SKIM COAT in as little as 1 hour. Coatings and epoxy toppings can be applied over SKIM COAT in 16 hours. Please comply with instructions from the floor covering manufacturer regarding substrate moisture and moisture testing. For sections deeper than 1" (2.5 cm), use Rapid Set® Cement All®, Rapid Set® Mortar Mix or Rapid Set® Concrete Mix. Conduct a minimum of one field test using the prepared substrate and finished floor covering to evaluate the suitability of the materials and procedures.

SURFACE PREPARATION: Application surfaces must be clean, sound and free from any materials that may inhibit bond, such as oil, dirt, mastic, asphalt, sealing compounds, acids, wax and loose debris. Smooth concrete surfaces should be mechanically abraded by scarifying, grinding, shot blasting or other approved methods. Acid etching is not recommended. Do not use solvents or adhesive removers as means of cleaning the substrate. Application surface must be between 50°F (10°C) and 90°F (32°C). In temperatures above 80°F (27°C), pre-wet the substrate with water before applying SKIM COAT. Honor all moving joints and cracks.

MIXING: Mix using a 1/2" drill with a mixing paddle or a margin trowel for small jobs. Use 4 quarts (3.8 L) of clean water per 20-lb (9.1-kg) bag. Place water in the mixing container. While mixing, add SKIM COAT. Mix for the minimum amount of time required to achieve a lump-free, uniform consistency (usually 1 to 3 minutes). Do not add additional water after initial mixing. For increased fluidity and workability, use Rapid Set® FLOW Control® plasticizing admixture from the Rapid Set® Concrete Pharmacy®. Contact CTS Cement for more information about the use of these additives.

PLACEMENT: Organize work so that all personnel and equipment are ready before placement. After mixing, place, consolidate and screed quickly to allow for maximum finishing time. Trowel and/or float to achieve desired finish as soon as possible. Do not install on frozen surfaces. To extend working time, use SET Control retarding admixture or cold mix water. SKIM COAT may be applied in temperatures ranging from 50°F (10°C) to 90°F (32°C). The working time of SKIM COAT is approximately 15 to 20 minutes at 70°F (21°C) ambient temperature.

HIGHLIGHTS

EXCELLENT BOND

Bonds to concrete, brick, block and more

VERSATILE

Apply featheredge to 1" (2.5 cm)

FAST SETTING

Workable for 20 minutes

Walk on in 1 hour

INTERIOR/EXTERIOR

Mold and mildew resistant

EASY TO USE

Just add water

No primer or curing compound required

CONFORMS TO:

ASTM C109

MANUFACTURER:

CTS Cement Manufacturing Corp.

11065 Knott Ave., Suite A

Cypress, CA 90630

Tel: 800-929-3030

Fax: 714-379-8270

Web: www.CTScement.com

E-mail: info@CTScement.com



SKIM COAT

For Patching, Skim Coating & Underlayments

COLD WEATHER: Environmental and material temperatures below 70°F (21°C) may delay setting time and reduce the rate of strength gain. Lower temperatures will have a more pronounced effect. Thinner sections will be more significantly affected. To compensate for cold temperatures, keep material warm, use heated mix water, and follow ACI 306 Procedures for Cold Weather Concreting.

WARM WEATHER: Environmental and material temperatures above 70°F (21°C) may speed setting time and increase the rate of strength gain. Higher temperatures will have a more pronounced effect. To compensate for warm temperatures, keep material cool, use chilled mix water, and follow ACI 305 Procedures for Hot Weather Concreting. The use of SET Control retarding admixture from the Concrete Pharmacy will help offset the effects of high temperatures.

CURING: SKIM COAT does not require water curing or curing compound under moderate conditions at 70°F (21°C). In dry, windy or hot conditions, mist with water to maintain a continuously wet surface until the product has achieved sufficient strength.

YIELD & PACKAGING: SKIM COAT is available in 20-lb (9.1-kg) bags. One 20-lb bag will yield approximately 67 ft² (6.2 m²) at 1/8" (0.3 cm) depth or 33 ft² (3.1 m²) at 1/4" (0.6 cm) depth. Coverage may vary due to jobsite conditions.

SHELF LIFE: SKIM COAT has a shelf life of 12 months when stored properly in a dry location, protected from moisture, out of direct sunlight, and in an undamaged package.

USER RESPONSIBILITY: Before using CTS products, read current technical data sheets, bulletins, product labels and safety data sheets at www.CTScement.com. It is the user's responsibility to review instructions and warnings for any CTS products prior to use.

WARNING: DO NOT BREATHE DUST. AVOID CONTACT WITH SKIN AND EYES. Use material in well-ventilated areas only. Exposure to cement dust may irritate eyes, nose, throat, and the upper respiratory system/lungs. Silica exposure by inhalation may result in the development of lung injuries and pulmonary diseases, including silicosis and lung cancer. Seek medical treatment if you experience difficulty breathing while using this product. The use of a NIOSH/MSHA-approved respirator (P-, N- or R-95) is recommended to minimize inhalation of cement dust. Eat and drink only in dust-free areas to avoid ingesting cement dust. Skin contact with dry material or wet mixtures may result in bodily injury ranging from moderate irritation and thickening/cracking of skin to severe skin damage from chemical burns. If irritation or burning occurs, seek medical treatment. Protect eyes with goggles or safety glasses with side shields. Cover skin with protective clothing. Use chemical resistant gloves and waterproof boots. In case of skin contact with cement dust, immediately wash off dust with soap and water to avoid skin damage. In case of skin contact with wet concrete, wash exposed skin areas with cold running water as soon as possible. In case of eye contact with cement dust, flush immediately and repeatedly with clean water, and consult a physician. If wet concrete splashes into eyes, rinse eyes with clean water for at least 15 minutes and go to the hospital for further treatment.

PROPOSITION 65 WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm.

Please refer to the SDS and www.CTScement.com for additional safety information regarding this material.

LIMITED WARRANTY: CTS CEMENT MANUFACTURING CORP. (CTS) warrants its materials to be of good quality and, at its option, will replace or refund the purchase price of any material proven to be defective within one (1) year from date of purchase. The above remedies shall be the limit of CTS's responsibility. Except for the foregoing, all warranties expressed or implied, including merchantability and fitness for a particular purpose, are excluded. CTS shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the materials.

PHYSICAL DATA

Set Time, ASTM C191

Initial set	25 minutes
Final set	40 minutes

Compressive Strength, ASTM C109 Mod.

3 hours	1000 psi (6.9 MPa)
24 hours	1500 psi (10.3 MPa)
7 days	2000 psi (13.8 MPa)
28 days	3000 psi (20.7 MPa)

All data produced at 70°F (21°C)



30% post consumer waste recycled fiber

USGBC and related logo is a trademark owned by the U.S. Green Building Council and is used by permission.